

## TECHNICAL DATA SHEET

PRODUCT IDENTIFICATION : BUSKAP

### TECHNICAL PROPERTIES

DESCRIPTION	STANDARD	PRODUCT				
		STARETTE	STONETTE	MAESTRO	DIGIKAP BUS	TRADITION
Design		STARETTE	STONETTE	MAESTRO	DIGIKAP BUS	TRADITION
Back Layer		TX150B	TX150B	TX150B	TX150B	TX150B
Total Thickness	EN ISO 24346	2.25 mm	2.25 mm	2.50 mm	2.50 mm	3.00 mm
Wear Layer Thickness	EN ISO 24340	0.50 mm	0.60 mm	0.50 mm	0.70 mm	1.00 mm
Mass per Unit Area	EN ISO 23997	2,606 gr/m <sup>2</sup>	2,571 gr/m <sup>2</sup>	3,006 gr/m <sup>2</sup>	2,936 gr/m <sup>2</sup>	3,621 gr/m <sup>2</sup>
Roll Width	EN ISO 24343	2	2	2	2	2
Roll Length	EN ISO 24343	20-24	20-24	20-24	20-24	20-24
Emboss		FR	PR	PR	PR	HR

### PERFORMANCE

Wear Group	EN 660-2	Group T	Group T	Group T	Group T	Group T
Binder Content	ISO 10582	Type 1	Type 1	Type 1	Type 1	Type 1
Effect of a castor chair	ISO 4918	No deformation after 25.000 cycles	No deformation after 25.000 cycles	No deformation after 25.000 cycles	No deformation after 25.000 cycles	No deformation after 25.000 cycles
Hot light fastness test	M3229	KF1	KF1	KF1	KF1	KF1
Dimensional Stability	EN ISO 23999	≤ 0.2	≤ 0.2	≤ 0.2	≤ 0.2	≤ 0.2
Curling	EN ISO 23999	1.2	1.2	1.2	1.2	1.2
Residual Indentation	EN ISO 24341-1	0.05	0.05	0.05	0.05	0.05
Flexibility	EN ISO 24344	No Crack	No Crack	No Crack	No Crack	No Crack
Fire Resistance	EN 13501-1	BF S1	BF S1	BF S1	BF S1	BF S1
Slip Resistance	DIN 51130	D5	D5	D5	D5	D5
Ball Drop Test	EN ISO 105-806	4	4	4	4	4
	DBL 53067.3	No Damage	No Damage	No Damage	No Damage	No Damage
Abrasion Resistance	DIN EN ISO 5470-1	% 1.00	% 1.00	% 1.00	% 1.00	% 1.00
Determination Of Staining And Resistance To Chemical	EN ISO 26987	Ok	Ok	Ok	Ok	Ok
Type Approval Approval By The United Kingdom Vehicle Approval Authority (VCA)	ECR-R 118.3	0 mm/min	0 mm/min	0 mm/min	0 mm/min	0 mm/min
Odour Test	VDA270	max. 3	max. 3	max. 3	max. 3	max. 3

\* Sipariş geçmeden önce, lütfen güncel TDS verilerini talep edin.

\* Before placing an order, please request up-to-date TDS data.

## TECHNICAL DATA SHEET

PRODUCT IDENTIFICATION: BUSKAP

### TECHNICAL PROPERTIES

DESCRIPTION	STANDARD	PRODUCT			
		NEOWOOD	SOMBRE	BUSWOOD	CAPTAIN
Design		NEOWOOD	SOMBRE	BUSWOOD	CAPTAIN
Back Layer		TX150B	TX150B	TX150B	TX150B
Total Thickness	EN ISO 24346	2.00 mm	2.25 mm	2.70 mm	3 mm
Wear Layer Thickness	EN ISO 24340	0.50 mm	0.50 mm	0.70 mm	0.60 mm
Mass per Unit Area	EN ISO 23997	2,207 gr/m <sup>2</sup>	2,606 gr/m <sup>2</sup>	3,236 gr/m <sup>2</sup>	3,772 gr/m <sup>2</sup>
Roll Width	EN ISO 24341	2	2	2	2
Roll Length	EN ISO 24341	20-24	20-24	20-24	20-24
Emboss		FR	FR	KB	P1
<b>PERFORMANCE</b>					
Wear Group	EN 660-2	Group T	Group T	Group T	Group T
Binder Content	ISO 10582	Type 1	Type 1	Type 1	Type 1
Effect of a castor chair	ISO 4918	No deformation after 25.000 cycles	No deformation after 25.000 cycles	No deformation after 25.000 cycles	No deformation after 25.000 cycles
Hot light fastness test	EN ISO 105-806	4	4	4	4
Dimensional Stability	EN ISO 23199	≤ 0.2	≤ 0.2	≤ 0.2	≤ 0.2
Curling	EN ISO 23199	1.2 mm	1.2 mm	1.2 mm	1.2 mm
Residual Indentation	EN ISO 24341-1	0.05 mm	0.05 mm	0.05 mm	0.05 mm
Flexibility	EN ISO 24344	No Crack	No Crack	No Crack	No Crack
Fire Resistance	EN 13501-1	Bfl S1	Bfl S1	Bfl S1	Bfl S1
Slip Resistance	DIN 51130	D5	D5	D5	D5
Ball Drop Test	DBL 53067.3	No Damage	No Damage	No Damage	No Damage
	M3229	KF1	KF1	KF1	KF1
Abrasion Resistance	DIN EN ISO 5470-1	% 1.00	% 1.00	% 1.00	% 1.00
Determination Of Staining And Resistance To Chemical	EN ISO 26987	Ok	Ok	Ok	Ok
Type Approval Approval By The United Kingdom Vehicle Approval Authority (VCA)	ECE-R 118.3	0 mm/min	0 mm/min	0 mm/min	0 mm/min
Odour Test	VDA270	max. 3	max. 3	max. 3	max. 3

\* Sipariş geçmeden önce, lütfen güncel TDS verilerini talep edin.

\* Before placing an order, please request up-to-date TDS data.